

**BITUMEN 50/70****GOST 33133-2014**

<b>QUALITY SPECIFICATIONS</b>			
	<b>PROPERTIES</b>	<b>GOST 33133-2014 Standard Limits</b>	<b>METHOD</b>
1	Penetration at 25 °C, 0,1 mm	51 - 70	GOST 33136
2	Ring-and-ball Softening Point, °C	min 51	GOST 33142
3	Ductility at 0 °C, cm	min 3,5	GOST 33138
4	Fraass Breaking Point	minus 16	GOST 33143
5	Flash Point, °C	min 230	GOST 33141
6	Change of Mass after RTFOT method, %	max 0,6	GOST 33140
7	Increase in Softening Point after RTFOT method, °C	max 7	GOST 33140, GOST 33142